

GLAZING OPTIONS	STYLE	SHGC	U-VALUE	U-FACTOR	ER	VT	CANADA ENERGY STAR ZONE
Cl-Arg-180	●	0.44	0.26	1.47	33	0.50	1,2
Cl-Arg-180, Div under 1"	●	0.40	0.26	1.49	30	0.45	1,2
180-Arg-Cl	●	0.41	0.26	1.47	31	0.50	1,2
180-Arg-Cl, Div under 1"	●	0.38	0.26	1.49	29	0.45	1,2
180-Arg-i89	●	0.40	0.23	1.30	34	0.49	1,2,3
180-Arg-i89, Div under 1"	●	0.36	0.23	1.30	32	0.44	1,2
Lami-Arg-180	●●	0.40	0.26	1.49	30	0.49	1,2
180-Arg-Cl-Arg-180	●●●	0.36	0.19	1.09	37	0.44	1,2,3
180-Arg-Cl-Arg-180, Div under 1"	●●●	0.33	0.19	1.10	35	0.40	1,2,3
180-ArgKry-Cl-ArgKry-180	●●●	0.36	0.17	0.98	39	0.44	1,2,3
180-ArgKry-Cl-ArgKry-180, Div under 1"	●●●	0.33	0.18	1.01	37	0.40	1,2,3
272-Cl-Arg-272	●●●	0.23	0.19	1.06	30	0.36	1,2,3
272-Cl-Arg-272, Div under 1"	●●●	0.21	0.19	1.08	28	0.33	1,2,3
272-ArgKry-Cl-ArgKry-272	●●●	0.23	0.18	1.04	30	0.36	1,2,3
272-ArgKry-Cl-ArgKry-272, Div under 1"	●●●	0.21	0.19	1.07	28	0.33	1,2,3
272-Kry-Cl-Kry-272	●●●	0.23	0.17	0.95	32	0.36	1,2,3
272-Kry-Cl-Kry-272, Div under 1"	●●●	0.21	0.17	0.98	30	0.33	1,2,3

Structural Ratings

AAMA/WDMA/CSA 101/1.S.2/A440-11 and A440S1-14
 Size Tested: 1220x1040mm (48" x 41")
 LC-PG70
 Positive Design Pressure = +3360 Pa
 Negative Design Pressure = -3360 Pa (-70 psf)
 Water Test Pressure: 510Pa
 Canadian Air Infiltration/Exfiltration: A3

Double Pane Glass ●
 Tri-pane Laminated Glass ●●
 Triple Pane Glass ●●●

